

Component – Plastics

E205256

STAR PLASTICS, INC

West Virginia, United States



MATERIAL DESIGNATION: PC7501 (F1)

Product Description: Polycarbonate (PC), furnished as pellets, (Colors: BK, GY, BG)

Color	Min Thk (mm)	Flame Class	HWI	HAI	RTI Elec	RTI IMP	RTI Str
(BK,GY,BG)	1.5	V-0	3	0	125	115	125
	2.5	V-0, 5VA	3	1	125	115	125
	3.0	V-0, 5VA	2	1	125	115	125
	3.8	V-0	-	-	125	115	125

Comparative Tracking Index (CTI): 2

Inclined Plane Tracking (IPT): --

Dielectric Strength (kV/mm): 24

Volume Resistivity (10⁹ohm-cm): 15

Dimensional Stability (%): 3

High Volt, Low Current Arc Resis (D495): 6

High-Voltage Arc Tracking Rate (HVTR): 0

(f1) – Suitable for outdoor use with respect to exposure to Ultraviolet Light, Water Exposure and Immersion in accordance with UL 746C

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliance, where the acceptability of the combination is determined by UL.

Last Revised: 2017-11-03

Access Date: 2018-07-06

2013 UL LLC©



IEC AND ISO TEST METHODS

Test Name	Test Method	Units	Thickness Tested (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	1.5	V-0 (BK,GY,BG)
			2.5	V-0,5VA (BK,GY,BG)
			3.0	V-0,5VA (BK,GY,BG)
			3.8	V-0 (BK,GY,BG)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	C	3.8	960
Glow-Wire Ignition (GWI)	IEC 60695-2-13	C	3.8	775
IEC Comparative Tracking Index	IEC 60112	Volts (max)	--	--
IEC Ball Pressure	IEC 60695-10-2	C	--	--
ISO Heat Deflection (1.80 MPa)	ISO 75-2	C	4.0	137
ISO Tensile Strength	ISO 527-2	MPa	--	--
ISO Flexural Strength	ISO 178	MPa	--	--
ISO Tensile Impact	ISO 8256	kJ/m ²	--	--
ISO Izod Impact	ISO 180	kJ/m ²	--	--
ISO Charpy Impact	ISO 179-2	kJ/m ²	--	--